



DSC891A

소재 특성

DESCO™ DSC891A는 PC와 ABS의 장점만을 선택적으로 이용한 Alloy Resin으로 강성 및 인성이 뛰어나고 저흡습성, 무광택, 도전성이 우수. 저변형으로 치수안정성이 뛰어난 제품입니다.

적용 분야

DESCO™ DSC891A 는 기계적 강도, 무광택 및 저변형성 특성을 요구하는 자동차 부품의 적용에 적합합니다.

작업 조건

본 제품은 제습 건조 후 밀봉되므로 성형 전 별도 건조과정이 필요 없습니다.

만약 수분이 함유되어 있을 경우에는 최소 100℃ 온도에서 3 시간 이상 제습 건조하여 수분 함유율이 0.2% 이하가 될 수 있도록 당부 드립니다.

[추천 성형 조건]

		UNIT	SETTING
수지 건조 온도		℃	100 ~ 120
수지 건조 시간		Hr	3 ~ 5
실린더	후부	℃	250 ~ 260
	중부	℃	260 ~ 270
	전부	℃	260 ~ 280
노즐 온도		℃	260 ~ 280
소재 온도		℃	260 ~ 280
금형 온도		℃	60 ~ 90
사출 속도		%	40 ~ 70
사출압력	1 st	%	30 ~ 60
	2 nd	%	30 ~ 60
보압		%	10 ~ 20

안전 자료

당사에서 제공하고 있는 물질안전보건자료(MSDS)를 참고하시기 바랍니다.



DSC891A

구 분	항 목	측정방법	단위	대표치
물리적 성질	수분 흡수율 (24hr water at 23°C)	ASTM D-570	%	-
	비중	ASTM D-792	-	1.11
	성형 수축율 (3t/100Ø 원판)	-	%	0.5~0.7
기계적 성질	인장 강도	ASTM D-638	Kgf/cm ²	550
	파단 신율	ASTM D-638	%	80
	굴곡 탄성률	ASTM D-790	Kgf/cm ²	22,000
	굴곡 강도	ASTM D-790	Kgf/cm ²	850
	Izod 충격강도	ASTM D-256	Kgf.cm/cm	70
	로크웰 경도(R-Scale)	ASTM D-785	-	-
열적 성질	융점	DSC	°C	-
	열변형 온도(1.8MPa)	ASTM D-648	°C	100
	열변형 온도(0.46MPa)	ASTM D-648	°C	-
	난 연 성	UL 94	-	HB
	체적 저항	ASTM D-257	Ohm.mm	-
전기적 성질	유전 상수(10 ⁶ Hz)	ASTM D-150	-	-
	절연 파괴 강도	ASTM D-149	KV/mm	-
	내아크성	ASTM D-495	Sec	-

☞ 제품 분류 code / PC+ABS

☞ 위 물성치는 당사에서 시험표준에 의하여 측정한 실험측정치이며 성형제품의 물성을 보증하기 위하여서는 별도의 데이터가 고려되어야 합니다.

This documentation is made out based on our tests and experiments in our R&D center with piled up experience and knowledge. And the values are measured on injection molded test specimens. It is suggested that this information contained in this document can be used for general indication. Therefore, you should not construe it as product specifications, and you should do appropriate test before you considering your conditions for newly applications.